

u/pst

10/533004
JC12 Rec'd PCT/PTC 28 APR 2005

#4/A
Sub-Spec
(DE)

BOARD PRODUCT AND METHOD OF MAKING THE SAME

BACKGROUND OF THE INVENTION

Field of the Invention

Embodiments of the present invention relate to a coated board product and a method of producing the same.

5 Description of Related Art

In the field of producing paper products, one ongoing goal is to improve the quality of board products, especially boxboard, and the economy of producing the same.

Board is required to have a certain surface quality for ensuring a desired gloss and print quality, a stiffness and tear resistance for securing the functionality of a package.

10 Since board is produced in large quantities in a board mill, the efficient use of raw material is also important. However, these demands are somewhat contradictory to each other. Board can be provided with a sufficient gloss by calendering the board by compressing it in a nip, often moistened and heated in a certain manner. The surface fibers and coating of board are preferably pressed smooth by this compression, yet
15 without compacting the middle ply of board. The compaction of a middle ply undermines board stiffness and reduces tear resistance. The compaction of a middle ply is often referred to as a loss of bulk. In this case, bulk is understood as being an inverse value to density and a loss thereof is thus equal to a densifying compaction of paper or board.

20 Since the process of making paper and board is highly raw material intensive, even a minor saving in raw material provides a major advantage over competitors. In this respect, a saving of just one percent can be considered a major competitive edge and the investment restitution time is short. Saving raw material is also desirable for

environmental reasons. By virtue of a reduced weight structure, the multiplicative effects of the board of this invention cover the product's entire life span, the reduced consumption of raw material resulting in a lighter container which ultimately creates savings also in shipping operations and in the way of a reduced amount of waste.

5 Packing boards are often coated and have a multi-ply structure. Coating and sizing are used for providing desired properties. A typical basis weight range for folding boxboards is 180-350 g/m². The necessary basis weight depends on a required stiffness of the package, a lighter board being sufficient for small boxes. Successful conservation of board bulk in surface treatment to produce thereby board of a higher stiffness results in
10 savings of raw material and energy by enabling the use of board of a lesser basis weight. Typical applications for board include cigarette packages, pharmaceutical packages, postcards, cardboard covers for books, various food packages.

Folding boxboards are often smoothed, prior to coating, with a Yankee cylinder, which enables a good bulk and stiffness, the surface properties being also good, the
15 drying shrinkage along the edges being likewise small, yet the use of a Yankee cylinder is limited by speed restraint, space demand for equipment and the enormous size of a Yankee cylinder in a high-speed machine. Another typical treatment method involves a wet-stack calender, the drawbacks of which include problems regarding runnability and a controlled application of water and, in addition, extra costs are incurred by the necessity
20 of drying the board before and after a calendering process.

A machine calender is often used together with other calenders, the machine calender referring to a hard calender with no elasticity in its rolls. The use of a machine calender as the sole surface treatment method is generally not advisable. A soft calender refers to a soft-nip calender, wherein the calender roll has a surface which is elastic, the
25 surface having possibly a hardness in the same order as the surface hardness of wood, yet being elastic.

BRIEF SUMMARY OF THE INVENTION

The above and other needs are met by the present invention which, in one
30 embodiment, provides a method of making a boxboard product with a smooth printing surface, a high gloss and stiffness in the boxboard with a lesser-than-before consumption

of material, and avoiding bottlenecks and improving runnability in the production process. In one embodiment, a coated packing board comprises two or more fiber plies, wherein the outside plies consist of bleached chemical pulp and the middle plies of mechanical pulp or chemithermo-mechanical pulp, recycled paper pulp, recycled cardboard pulp or broke. The body consists typically of recycled mixed pulp, the body and the top surface having therebetween a protective ply which typically consists of deinked pulp (DIP), white ledger, chemithermo-mechanical pulp (CTMP) or mechanical pulp (GW). The middle ply may have a core which consists for example of old corrugated containers (OCC), mixed waste paper pulp (MW), old newspapers (ONP), groundwood (SGW, PGW) or broke. The backing comprises for example bleached chemical pulp or chemithermo-mechanical pulp. In any case, the purpose of a multi-ply structure is to create a surface with good printing qualities, a dark recycled material being good enough for the middle ply. A typical basis weight range is 200-400 g/m². The structure of a typical boxboard is illustrated in **FIG. 4**.

Generally, the pretreatment of a boxboard surface prior to a coating process is performed with a machine calender and/or a Yankee cylinder. The function of a machine calender is to provide the web with a uniform thickness profile. Smoothing of the surface is performed with a Yankee cylinder.

However, according to embodiments of the invention, boxboard is treated with a long-nip calender prior to coating in order to upgrade the board qualities over what is known before and, in addition, the production runnability is improved and the production method is not subject to a speed restraint in the same way as an arrangement using a Yankee cylinder. A long-nip calender suitable for making a board according to the invention has been described, for example, in U.S. Patent No. 6,164,198 also assigned to the assignee of the present invention.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING(S)

Having thus described the invention in general terms, reference will now be made to the accompanying drawings, which are not necessarily drawn to scale, and wherein:

FIG. 1 is a sectional view of a long-nip calender, provided with an extended nip between an enclosed shoe calender and a counter roll;

FIG. 1A is a partial enlargement of **FIG. 1**;

FIG. 2A is a partial sectional view of the device shown in **FIG. 1**, along the roll axis and depicting a drive mechanism;

FIG. 2B shows the operation of press shoes in a longitudinal section;

5 **FIG. 3** shows measuring results for test parcels in graphic representation; and

FIG. 4 shows the structure of a typical boxboard in a schematic view.

DETAILED DESCRIPTION OF THE INVENTION

The present inventions now will be described more fully hereinafter with
10 reference to the accompanying drawings, in which some, but not all embodiments of the inventions are shown. Indeed, these inventions may be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will satisfy applicable legal requirements. Like numbers refer to like elements throughout.

15 A calender suitable for the surface treatment of a board of the invention is shown in **FIGS. 1-2** to include a fixed support element **14**, around which is a tubular jacket **12**. A heated counter element **22** is disposed on the other side of the tubular jacket **12** from the support element, such that a web passes through between said counter element and the tubular jacket. The fixed support element is provided with load elements **18, 20**,
20 applying the jacket **12** against the heated counter element **22** and thereby enabling a calendering process between the jacket and the counter element. The jacket has its opposite ends secured to end walls **24, 26** mounted rotatably relative to the support element, the rotary motion of the end walls being delivered by a separate drive motor, which is independent of a motion of the fiber web in order to avoid overheating of the
25 jacket. The drive motor is shown in the figure in dashed lines.

A method of the invention for conditioning the surface of coated or uncoated board with a surface conditioning device is in turn characterized in that the method comprises feeding a fiber web through an extended nip established by a roll and a counter-roll, the former being in the form of a tubular-shaped flexible jacket. Across the
30 extent of the nip the jacket deflects and thereby presses into contact with the counter-roll over a long stretch. The board treated with the method is lighter than currently available

boards, while stiffness and surface properties are equal to those of currently available boards.

The solution enables a running speed substantially higher than what is accomplished with a Yankee-cylinder equipped board machine. In addition, the
5 runnability is better, this also contributing to improved quality and reducing waste.

Web speed in the calender may be higher than 600 m/min, preferably higher than 800 m/min, and still more preferably 1000 m/min, and even as high as about 4000 m/min. Thus, the calender does not restrict the speed of a board machine. The above-mentioned heated roll has a temperature of 150-350°C, preferably higher than 170°C, most
10 preferably about 200-250°C. Linear pressure in the nip is within the range of 100-500 kN/m, preferably less than 400 kN/m, most preferably about 50-300 kN/m. Maximum pressure in the nip is 3-15 MPa, preferably less than 13 MPa, most preferably about 0.5-8 MPa.

In **FIG. 1**, a board web **80** travels through an extended and heated nip **1**. The nip
15 **1** is established by an enclosed shoe roll **10** present under the web **80**. Above the web **80** is a heatable counter-roll **22**. The enclosed shoe roll **10** comprises a flexible jacket **12** impervious to liquid. The jacket consists for example of fiber-reinforced polyurethane. The stationary fixed support element **14** carries at least one load shoe **18**. Between the load shoe **18** and the support element is an actuator **20**, such as a hydraulic cylinder, for
20 urging the concave load shoe **18** and thereby also the flexible jacket **12** against the counter-roll **22**. Thus, the jacket **12** is forced out of its normal unloaded position **11** in a direction away from the center of the enclosed shoe roll. The jacket **12** is fastened at both ends thereof to end walls **24**, **26**, thus creating a sealed compartment **13** (see **FIG. 2**). As shown also in **FIG. 1**, at least one detector device **99** is mounted in communication with
25 the web **80** for detecting web breaks. The detector device **99** is connected to a control device **98** for controlling the operation of a calendering process in dependence of the web being broken or not.

As shown in **FIG. 1**, the heatable counter-roll **22** is accompanied by a disengagement mechanism, comprising a lever **95** pivotable by a hydraulic cylinder
30 assembly **94** and provided with a pivot point **96** for pivoting the lever thereon. The

disengagement mechanism presses the counter-roll 22 to an engagement with the nip 1 and disengages it from the nip 1.

Between the load shoe 18 and the jacket 12 is supplied a pressurized oil, which develops a hydrostatic pressure throughout the nip and presses the jacket to an
5 engagement with the counter-roll 22 over the entire extent of the nip 1. At the same time, the oil protects the jacket from being damaged by lumps and a temperature rise.

In FIG. 2A it is shown that the end walls 24, 26 are rotatably mounted on stub shafts 16, 17 of the support element 14 (The end walls are preferably not integral but divided into a static part and a rotating part as shown in FIG. 2B). On one end of the
10 stub shaft, a cylindrical shaft 32 is arranged rotatably via bearings 34. A support column 36 is arranged to the cylindrical shaft via self-aligning bearings 38, which allow spherical movement to allow the deformation/bending of the support element 14 when heavily loaded. One of the end walls 24 is fixedly attached to the cylindrical shaft. A drive transmission 40 is fixedly attached to the cylindrical shaft outside the end wall, in the
15 shown embodiment a cog wheel. The cog wheel is connected to a transmission 42 and in turn a drive 44. A cog wheel 46 is fixedly attached to the cylindrical shaft inside the end wall. A drive shaft 48 is arranged inside the jacket and parallel to the support element 14. The drive shaft 48 is supported by bearings 50 arranged in bearing houses 52 attached to the support element. At each end of the drive shaft, cog wheels 54 are arranged.
20 Preferably these cog wheels have a prolonged toothed portion to allow axial movement of the intermeshing cog wheel which is attached to the end wall. A further cog wheel 56 is fixedly attached to the second end wall 26 inside the jacket. Both cog wheels inside the jacket mesh with the corresponding cog wheel on the drive shaft. The second end wall 26 is rotatably arranged on the second stub shaft 17. The second stub shaft is in turn
25 fixedly attached to a second support column 58.

The operation is as follows. During normal operation, the driven heated roll 22 is in interaction with the fiber web and the flexible jacket 12 by a desired pressure being exerted by the load shoe 18, thereby causing a friction based drive of both the fiber web and the flexible jacket. Accordingly, during normal operation the forces exerted in the
30 nip provide for rotation of the enclosed shoe roll.

Only in specific occasions, it will normally be desirable to operate the independent drive of the enclosed shoe roll 10, for example when starting up the calender. If the calender should be started without first speeding up the flexible jacket 12, this would inevitably cause damage to the flexible jacket due to overheating.

5 Furthermore, it would also be deteriorating for the fiber web, since at the moment of start it would develop exceptional tension forces in the fiber web. Accordingly, the independent drive arrangement of the enclosed shoe roll is to be used for instance at the start-up of the calendering surface. At the start, the nip gap is not closed, but the roll 22 has been moved out of contact with the nip 1. Before moving the heated counter-roll 22
10 into the nip, the drive arrangement 44 of the enclosed shoe roll 10 is activated to accelerate the first end wall 24 via transmissions. The rotation of the end wall causes the inner first cog wheel 46 to rotate, and subsequently the drive shaft 48. The drive shaft transmits the rotation to the second end wall 26 via the second inner cog wheel 56. The both end walls are thus accelerated and rotate at the same speed until a desired peripheral
15 speed is obtained, which is normally equal to the speed of the fiber web. The nip is closed by activating the hydraulic piston 94 to pivot the lever 95 and thereby moving the counter-roll 22 into the nip and subsequently the load shoe 18 is urged against the heated roll 22 by its actuators 20. Once the calender functions in the desired manner, the drive arrangement of the enclosed shoe roll can be deactivated and the press roll driven in a
20 conventional manner by friction within the nip 1.

In **FIG. 2B** there is shown an alternative embodiment of the drive arrangement for an enclosed shoe roll. This embodiment uses friction for the transmission of rotational forces.

FIG. 2B also shows a design of arranging the support element and the end walls.
25 The end walls are divided into inner parts 24A, 26A connected non-rotatably to the support element 14, a rotational part 24B, 26B, and a bearing assembly 24C, 26C therebetween. The support element 14 is at its ends arranged with self-aligning bearings 23, 25 to allow a deflection of the support element 14.

In the figure there is shown a drive 44 having a shaft 19B. On the shaft 19B is
30 mounted a disc 19 having a rubber layer at its peripheral end 19A. The outer ends of the flexible jacket 12 are fixedly attached between an annular ring 15, acting as a replaceable

force transmitting device, and the periphery of each end wall. The ring 15 is fixedly attached to the end wall. On the inside of the rotational part 24B, 26B of each end wall there is fixedly attached a cog wheel 46, 56. The drive arrangement 44, 19 is movable in and out of contact with the force transmitting device 15. When it is desired to accelerate the enclosed shoe roll 10, the drive arrangement is moved such that the rubber layer 19A comes into frictional engagement with the force transmitting device 15. The cog wheel 46 and the drive shaft 48 transmit the rotation of the end wall 24 to the other end wall 26 by the cog wheels 54, 55 and 56, which at the same time function as a synchronizing device. Hence, both end walls 24, 26 are operated as described in reference to FIG. 2A. FIG. 2B further illustrates in a schematic view of one functional embodiment of the load shoe 18. The load shoe 18 is not disposed diametrically relative to the drive shaft, but perpendicularly as in FIG. 2A.

Tests conducted by the assignee indicated that, in test batches manufactured by a long-nip calender as described above, the board could be provided with a ratio of bulk and smoothness better than in currently available types of board. Thus, according to measurements, the goals of the invention are achieved.

Shoe calenders can be driven at high speeds and, furthermore, by the application of an elevated temperature, e.g. about 250°C, and by taking into account a long dwell time in the calendering zone, the resulting gloss finish will be equal to what is achieved in a slower solution using a Yankee cylinder. In addition, the board is provided with improved bulk. In addition to aspects contributing directly to board quality, the results include savings of production space in a mill, the elimination of a production limiting Yankee cylinder, and the provision of a more manageable, more easily controlled system.

In view of producing board of the invention, surface moistening can be provided prior to calendering. However, the board can also be produced without surface moistening.

Pilot tests were conducted for comparing a board manufactured on a normal Yankee cylinder with a board produced with the same machine, which was not smoothed by a Yankee cylinder, but which was calendered in pilot conditions by a shoe calender as described above. As a reference, the same board was also calendered with a soft calender.

FIG. 3 illustrates the ratio of Bendtsen roughness to obtained bulk. The grades treated by a shoe calender are designated with the word shoe, those manufactured by a soft-nip calender with the word soft. The degrees refer to a calendering temperature and the symbol reference is used to refer to a grade of board manufactured with a Yankee cylinder. A clear trend is observed, according to which the majority of results measured on a shoe calender lies within a high bulk and smooth range, Bendtsen roughness is about 500 ml/min or less, while bulk is more than 1.40. The board smoothed with a Yankee cylinder is smooth in terms of roughness, about 300 ml/min, but its bulk is only in the order of 1.29. Though these results were obtained in pilot conditions, experience indicates that the results should also improve in production conditions.

The measurements relate to precalendering results prior to coating. After a coating process, the method is capable of producing board, which has a basis weight of 150-500 g/m², PPS-s10 roughness (ISO 8791-4) 0.8 – 3.0 µm, Hunter gloss (ISO/DIS 8254) 30-80%, and a density (SCAN-P7:75) of 500-1000 kg/m³.

Compared with prior known grades, the obtained board is higher in bulk and smooth and, in addition, the production method is not speed restricted the same way as with a Yankee cylinder. The method provides saving in board manufacture and improves economy. Especially, the increase of capacity is possible with the same board machine by on-line calendering. In the case of a new mill, space is also saved in comparison with a Yankee cylinder. The provision of higher bulk represents a direct saving in terms of the amount of material and energy needed for production, the lighter packing board saving likewise energy over its service life and ultimately producing less waste.

Many modifications and other embodiments of the inventions set forth herein will come to mind to one skilled in the art to which these inventions pertain having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is to be understood that the inventions are not to be limited to the specific embodiments disclosed and that modifications and other embodiments are intended to be included within the scope of the appended claims. Although specific terms are employed herein, they are used in a generic and descriptive sense only and not for purposes of limitation.